



253 Polaris Ave. Mountain View CA 94043

TYPICAL PHYSICAL PROPERTIES
KOROKLEAR VINYL STRIP AND SHEET

SPECIFIC GRAVITY	ASTM D-792	1.25
TENSILE STRENGTH, PSI	ASTM D-412	2400
ULTIMATE ELONGATION, %	ASTM D-412	370
100% MODULUS, PSI	ASTM D-412	1400
TEAR RESISTANCE #/IN.	ASTM D-1004	325
SPECULAR TRANSMISSION	ASTM D-1746	80 - 90
STIFFNESS @ + 20 F, PSI	ASTM D-747	6,500
@ - 20 F, PSI		44,000
BRITTLE POINT, F	ASTM D-746	-20
HARDNESS, SHORE A	ASTM D-2240	81

IMPORTANT: WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE,
BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.